## DATA SHEET:

Governing Units: Metric

## TS Peak M3 10.5 (1.382) 1635



		4		
Mechanical Specifications	Metric		Imperial	
Fully Annealed AI Cross-sectional Area*	828.41	mm <sup>2</sup>	1634.83	kcmil
Encapsulated Aluminum Cross-Sectional Area	127.23	mm <sup>2</sup>	0.19721	in <sup>2</sup>
Diameter of Composite Core (Exclude Encapsulation)	10.5	mm	0.41300	in
Cross-sectional Area of Core (Exclude Encapsulation)	86.60	mm <sup>2</sup>	0.13421	in <sup>2</sup>
Overall Diameter of Conductor	35.103	mm	1.382	in
Cross-sectional Area of the Conductor (Exclude Covering)	915.00	mm <sup>2</sup>	1.41825	in <sup>2</sup>
Ultimate Tensile Strength of Conductor 1) ,2)	287.09	kN	64.54	kip
Rated Strength of Core - 399 ksi (2750 MPa)	238.11	kN	53.53	kip
Core Mass per unit length (Exclude Encapsulation)	151.00	kg/km	101.48	lb/kft
Conductor Mass per unit length	2434.94	kg/km	1636.48	lb/kft
Fully Annealed AlMass per unit length (Include Encapsulation)**	2283.94	kg/km	1535.00	lb/kft
Maximum Emergency Temperature at Surface 3)	200	°C	392	°F
Coefficient of Linear Expansion Above Thermal Kneepoint (core)	0.500	x10 <sup>-6</sup> /°C	0.278	x10 <sup>-6</sup> /⁰F
Coefficient of Linear Expansion Below Thermal Kneepoint (conductor)	18.066	x10 <sup>-6</sup> /°C	10.037	x10 <sup>-6</sup> /⁰F
Final Modulus of Elasticity Above Thermal Kneepoint (based on core area)	150.0	GPa	21.8	Msi
Final Modulus of Elasticity Below Thermal Kneepoint (based on conductor area)	64.3	GPa	9.3	Msi
Aluminum Heat Capacity	2123.5	Watt-s/m-°C	359.6	Watt-s/ft-°F
Core Heat Capacity	128.1	Watt-s/m-°C	21.7	Watt-s/ft-°F
Encapsulation Thickness	3.00	mm	0.11811	in
Stranding Ratio	1.0260			
Covered Thickness	0.000	mm	0.000	in
Electrical Specifications	Metric		Imperial	
DC Resistance at 20°C (Fully Annealed Al 63% IACS)	0.0338	ohm/km	0.0543	ohm/mile
DC Resistance at 25°C	0.0344	ohm/km	0.0554	ohm/mile
DC Resistance at 75°C	0.0413	ohm/km	0.0665	ohm/mile
Temperature Coefficient of Resistance at 20°C	0.00408	1/°C	0.00227	1/°F
Frequency	60	Hz	60	Hz
AC Resistance at 25°C	0.0366	ohm/km	0.0589	ohm/mile
AC Resistance at 75°C	0.0432	ohm/km	0.0695	ohm/mile
AC Resistance at 180°C	0.0569	ohm/km	0.0916	ohm/mile
Ampacity 4)		2392	@180°C, & A	
		2530	@200°C, & A	
GMR (estimated)	14.16	mm	0.0465	ft
Inductive Reactance (Xa: internal flux+external flux radius 1 ft)	0.2314	ohm/km	0.372	ohm/mile
	1	Mohm-km	0.085	Mohm-mile

\*TS Peak M3 10.5 (1.382) 1635 conductor is produced with Fully Annealed Al aluminum. The nominal Aluminum equivaeInt area is 828.4 sq. mm (1634.8 kcmil)

\*\*TS® Conductors are required to exhibit lay lengths (ratios) that conform to established ACSR and ACSS standards.

1) Fully Annealed AI rated tensile strength based on applicable standard. Core tensile strength based on 100% of its strength.

2) Strength at ambient temperature, Strength may be reduced to Rated Core Strength when temperature is above knee point

3) Maximum continuous operating temperature of TS Peak M3 10.5 (1.382) 1635 is 180°C and a maximum emergency temperature of 200°C

4). Ampacity based on: 25°C ambient temperature, 2ft/s (0.6 m/s) perpendicular wind, 0.5 Emis 0.5 Absorb.60 Hz, sea level (0) elevation, 30°N line Azimuth, noon on June 10th (96W/sq.ft, 1033W/sq.m), clear atmosphere

The information contained herein is offered in good faith. All values are nominal unless specifically indicated as maximum or minimum. The actual configuration of a given size may vary between conductor manufacturers and may result in slight variations in some of the indicated values. Data herein is to be considered confidential and proprietary to TS Conductor

contact: info@tsconductor.com

ID:29736 Date Produced: 3/4/2024