

## DATA SHEET:

## 1090 KCMIL\_Zenobia\_AECC\_TW\_M3\_TS



Governing Units: Metric

Mechanical Specifications	Metric		Imperial	
Fully Annealed Al Cross-sectional Area*	552.16	mm <sup>2</sup>	1089.68	kcmil
Encapsulated Aluminum Cross-Sectional Area	95.00	mm <sup>2</sup>	0.14725	in <sup>2</sup>
Diameter of Composite Core (Exclude Encapsulation)	8.5	mm	0.33500	in
Cross-sectional Area of Core (Exclude Encapsulation)	56.70	mm <sup>2</sup>	0.08795	in <sup>2</sup>
Overall Diameter of Conductor	28.620	mm	1.127	in
Cross-sectional Area of the Conductor (Exclude Covering)	608.90	mm <sup>2</sup>	0.94381	in <sup>2</sup>
Ultimate Tensile Strength of Conductor 1) ,2)	188.83	kN	42.45	kip
Rated Strength of Core - 399 ksi (2750 MPa)	156.00	kN	35.07	kip
Core Mass per unit length (Exclude Encapsulation)	99.00	kg/km	66.54	lb/kft
Conductor Mass per unit length	1616.67	kg/km	1086.54	lb/kft
Fully Annealed Al Mass per unit length (Include Encapsulation)**	1517.67	kg/km	1020.00	lb/kft
Maximum Emergency Temperature at Surface 3)	200	°C	392	°F
Coefficient of Linear Expansion Above Thermal Kneepoint (core)	0.500	x10 <sup>-6</sup> /°C	0.278	x10 <sup>-6</sup> /°F
Coefficient of Linear Expansion Below Thermal Kneepoint (conductor)	18.141	x10 <sup>-6</sup> /°C	10.078	x10 <sup>-6</sup> /°F
Final Modulus of Elasticity Above Thermal Kneepoint (based on core area)	150.0	GPa	21.8	Msi
Final Modulus of Elasticity Below Thermal Kneepoint (based on conductor area)	64.3	GPa	9.3	Msi
Aluminum Heat Capacity	1415.4	Watt-s/m-°C	239.7	Watt-s/ft-°F
Core Heat Capacity	83.9	Watt-s/m-°C	14.2	Watt-s/ft-°F
Encapsulation Thickness	2.70	mm	0.10630	in
Stranding Ratio	1.0225			
Covered Thickness	0.000	mm	0.000	in
Electrical Specifications	Metric		Imperial	
DC Resistance at 20°C (Fully Annealed Al 63% IACS)	0.0505	ohm/km	0.0812	ohm/mile
DC Resistance at 25°C	0.0515	ohm/km	0.0829	ohm/mile
DC Resistance at 75°C	0.0618	ohm/km	0.0995	ohm/mile
Temperature Coefficient of Resistance at 20°C	0.00408	1/°C	0.00227	1/°F
Frequency	60	Hz	60	Hz
AC Resistance at 25°C	0.0530	ohm/km	0.0853	ohm/mile
AC Resistance at 75°C	0.0631	ohm/km	0.1015	ohm/mile
AC Resistance at 180°C	0.0842	ohm/km	0.1355	ohm/mile
Ampacity 4)		1843	@180°C, & A	
		1945	@200°C, & A	
GMR (estimated)	11.54	mm	0.0379	ft
Inductive Reactance (Xa: internal flux+external flux radius 1 ft)	0.2468	ohm/km	0.397	ohm/mile
Capacitive Reactance	0.1460	Mohm-km	0.091	Mohm-mile

\*1090 KCMIL\_Zenobia\_AECC\_TW\_M3\_TS conductor is produced with Fully Annealed Al aluminum. The nominal Aluminum equivalent area is 552.2 sq. mm (1089.7 kcmil)

\*\*TS® Conductors are required to exhibit lay lengths (ratios) that conform to established ACSR and ACSS standards.

- 1) Fully Annealed Al rated tensile strength based on applicable standard. Core tensile strength based on 100% of its strength.
- 2) Strength at ambient temperature, Strength may be reduced to Rated Core Strength when temperature is above knee point
- 3) Maximum continuous operating temperature of 1090 KCMIL\_Zenobia\_AECC\_TW\_M3\_TS is 180°C and a maximum emergency temperature of 200°C
- 4). Ampacity based on: 25°C ambient temperature, 2ft/s (0.6 m/s) perpendicular wind, 0.5 Emis 0.5 Absorb.60 Hz, sea level (0) elevation, 30°N line Azimuth, noon on June 10th (96W/sq.ft, 1033W/sq.m), clear atmosphere

The information contained herein is offered in good faith. All values are nominal unless specifically indicated as maximum or minimum. The actual configuration of a given size may vary between conductor manufacturers and may result in slight variations in some of the indicated values. Data herein is to be considered confidential and proprietary to TS Conductor

contact: info@tsconductor.com

ID:50555

Date Produced:

6/3/2025