

DATA SHEET:

1094 KCMIL_Pennell_AECC_TW_M3_TS



Governing Units: Metric

Mechanical Specifications	Metric		Imperial	
Fully Annealed Al Cross-sectional Area*	554.41	mm ²	1094.11	kcmil
Encapsulated Aluminum Cross-Sectional Area	112.97	mm ²	0.17511	in ²
Diameter of Composite Core (Exclude Encapsulation)	9.5	mm	0.37400	in
Cross-sectional Area of Core (Exclude Encapsulation)	70.90	mm ²	0.10987	in ²
Overall Diameter of Conductor	28.956	mm	1.140	in
Cross-sectional Area of the Conductor (Exclude Covering)	625.30	mm ²	0.96920	in ²
Ultimate Tensile Strength of Conductor 1) ,2)	228.24	kN	51.31	kip
Rated Strength of Core - 399 ksi (2750 MPa)	194.92	kN	43.82	kip
Core Mass per unit length (Exclude Encapsulation)	123.00	kg/km	82.67	lb/kft
Conductor Mass per unit length	1645.13	kg/km	1105.67	lb/kft
Fully Annealed Al Mass per unit length (Include Encapsulation)**	1522.13	kg/km	1023.00	lb/kft
Maximum Emergency Temperature at Surface 3)	200	°C	392	°F
Coefficient of Linear Expansion Above Thermal Kneepoint (core)	0.500	x10 ⁻⁶ /°C	0.278	x10 ⁻⁶ /°F
Coefficient of Linear Expansion Below Thermal Kneepoint (conductor)	17.271	x10 ⁻⁶ /°C	9.595	x10 ⁻⁶ /°F
Final Modulus of Elasticity Above Thermal Kneepoint (based on core area)	150.0	GPa	21.8	Msi
Final Modulus of Elasticity Below Thermal Kneepoint (based on conductor area)	66.4	GPa	9.6	Msi
Aluminum Heat Capacity	1421.2	Watt-s/m-°C	240.7	Watt-s/ft-°F
Core Heat Capacity	104.8	Watt-s/m-°C	17.8	Watt-s/ft-°F
Encapsulation Thickness	2.90	mm	0.11417	in
Stranding Ratio	1.0225			
Covered Thickness	0.000	mm	0.000	in
Electrical Specifications	Metric		Imperial	
DC Resistance at 20°C (Fully Annealed Al 63% IACS)	0.0502	ohm/km	0.0809	ohm/mile
DC Resistance at 25°C	0.0513	ohm/km	0.0825	ohm/mile
DC Resistance at 75°C	0.0615	ohm/km	0.0990	ohm/mile
Temperature Coefficient of Resistance at 20°C	0.00408	1/°C	0.00227	1/°F
Frequency	60	Hz	60	Hz
AC Resistance at 25°C	0.0527	ohm/km	0.0848	ohm/mile
AC Resistance at 75°C	0.0627	ohm/km	0.1009	ohm/mile
AC Resistance at 180°C	0.0837	ohm/km	0.1348	ohm/mile
Ampacity 4)		1855	@180°C, & A	
		1958	@200°C, & A	
GMR (estimated)	11.76	mm	0.0386	ft
Inductive Reactance (Xa: internal flux+external flux radius 1 ft)	0.2454	ohm/km	0.395	ohm/mile
Capacitive Reactance	0.1455	Mohm-km	0.090	Mohm-mile

*1094 KCMIL_Pennell_AECC_TW_M3_TS conductor is produced with Fully Annealed Al aluminum. The nominal Aluminum equivalent area is 554.4 sq. mm (1094.1 kcmil)

**TS® Conductors are required to exhibit lay lengths (ratios) that conform to established ACSR and ACSS standards.

- 1) Fully Annealed Al rated tensile strength based on applicable standard. Core tensile strength based on 100% of its strength.
- 2) Strength at ambient temperature, Strength may be reduced to Rated Core Strength when temperature is above knee point
- 3) Maximum continuous operating temperature of 1094 KCMIL_Pennell_AECC_TW_M3_TS is 180°C and a maximum emergency temperature of 200°C
- 4). Ampacity based on: 25°C ambient temperature, 2ft/s (0.6 m/s) perpendicular wind, 0.5 Emis 0.5 Absorb.60 Hz, sea level (0) elevation, 30°N line Azimuth, noon on June 10th (96W/sq.ft, 1033W/sq.m), clear atmosphere

The information contained herein is offered in good faith. All values are nominal unless specifically indicated as maximum or minimum. The actual configuration of a given size may vary between conductor manufacturers and may result in slight variations in some of the indicated values. Data herein is to be considered confidential and proprietary to TS Conductor

contact: info@tsconductor.com

ID:26317


Date Produced:

6/3/2025

TS[®] Conductor Cross sectional drawing

Drawing for customers

Expected value at production time



TS Conductor Corp.

TS Pennell M3 9.5 (1.14) 1094 ID: 26317

Design

Check

Ratify