

## DATA SHEET:

**385 KCMIL\_GoatRock\_AECC\_TW\_M3\_TS**

Governing Units: Metric

Mechanical Specifications	Metric		Imperial	
Fully Annealed Al Cross-sectional Area*	194.85	mm <sup>2</sup>	384.53	kcmil
Encapsulated Aluminum Cross-Sectional Area	50.14	mm <sup>2</sup>	0.07772	in <sup>2</sup>
Diameter of Composite Core (Exclude Encapsulation)	5.5	mm	0.21700	in
Cross-sectional Area of Core (Exclude Encapsulation)	23.80	mm <sup>2</sup>	0.03683	in <sup>2</sup>
Overall Diameter of Conductor	17.094	mm	0.673	in
Cross-sectional Area of the Conductor (Exclude Covering)	218.60	mm <sup>2</sup>	0.33885	in <sup>2</sup>
Ultimate Tensile Strength of Conductor 1) ,2)	77.22	kN	17.36	kip
Rated Strength of Core - 399 ksi (2750 MPa)	65.30	kN	14.68	kip
Core Mass per unit length (Exclude Encapsulation)	41.00	kg/km	27.56	lb/kft
Conductor Mass per unit length	575.16	kg/km	386.56	lb/kft
Fully Annealed Al Mass per unit length (Include Encapsulation)**	534.16	kg/km	359.00	lb/kft
Maximum Emergency Temperature at Surface 3)	200	°C	392	°F
Coefficient of Linear Expansion Above Thermal Kneepoint (core)	0.500	x10 <sup>-6</sup> /°C	0.278	x10 <sup>-6</sup> /°F
Coefficient of Linear Expansion Below Thermal Kneepoint (conductor)	17.502	x10 <sup>-6</sup> /°C	9.723	x10 <sup>-6</sup> /°F
Final Modulus of Elasticity Above Thermal Kneepoint (based on core area)	150.0	GPa	21.8	Msi
Final Modulus of Elasticity Below Thermal Kneepoint (based on conductor area)	66.3	GPa	9.6	Msi
Aluminum Heat Capacity	499.5	Watt-s/m-°C	84.6	Watt-s/ft-°F
Core Heat Capacity	35.1	Watt-s/m-°C	6.0	Watt-s/ft-°F
Encapsulation Thickness	2.10	mm	0.08268	in
Stranding Ratio	1.0200			
Covered Thickness	0.000	mm	0.000	in
Electrical Specifications	Metric		Imperial	
DC Resistance at 20°C (Fully Annealed Al 63% IACS)	0.1425	ohm/km	0.2294	ohm/mile
DC Resistance at 25°C	0.1454	ohm/km	0.2341	ohm/mile
DC Resistance at 75°C	0.1745	ohm/km	0.2808	ohm/mile
Temperature Coefficient of Resistance at 20°C	0.00408	1/°C	0.00227	1/°F
Frequency	60	Hz	60	Hz
AC Resistance at 25°C	0.1459	ohm/km	0.2349	ohm/mile
AC Resistance at 75°C	0.1749	ohm/km	0.2815	ohm/mile
AC Resistance at 180°C	0.2358	ohm/km	0.3795	ohm/mile
Ampacity 4)		939	@180°C, & A	
		987	@200°C, & A	
GMR (estimated)	6.93	mm	0.0227	ft
Inductive Reactance (Xa: internal flux+external flux radius 1 ft)	0.2853	ohm/km	0.459	ohm/mile
Capacitive Reactance	0.1706	Mohm-km	0.106	Mohm-mile

\*385 KCMIL\_GoatRock\_AECC\_TW\_M3\_TS conductor is produced with Fully Annealed Al aluminum. The nominal Aluminum equivalent area is 194.9 sq. mm (384.5 kcmil)

\*\*TS® Conductors are required to exhibit lay lengths (ratios) that conform to established ACSR and ACSS standards.

- 1) Fully Annealed Al rated tensile strength based on applicable standard. Core tensile strength based on 100% of its strength.
- 2) Strength at ambient temperature, Strength may be reduced to Rated Core Strength when temperature is above knee point
- 3) Maximum continuous operating temperature of 385 KCMIL\_GoatRock\_AECC\_TW\_M3\_TS is 180°C and a maximum emergency temperature of 200°C
- 4). Ampacity based on: 25°C ambient temperature, 2ft/s (0.6 m/s) perpendicular wind, 0.5 Emis 0.5 Absorb. 60 Hz, sea level (0) elevation, 30°N line Azimuth, noon on June 10th (96W/sq.ft, 1033W/sq.m), clear atmosphere

The information contained herein is offered in good faith. All values are nominal unless specifically indicated as maximum or minimum. The actual configuration of a given size may vary between conductor manufacturers and may result in slight variations in some of the indicated values. Data herein is to be considered confidential and proprietary to TS Conductor

contact: info@tsconductor.com

ID:50510

Date Produced:

6/3/2025